



An ISO:9001:2015, ISO:14001:2015, ISO:45001:2018 Certified Laboratory

TEST REPORT

Issued To: M/S HASHCART INDIA Plot No.- 42, Dasna, Sadbhawana Enclave, Ghaziabad Uttar Pradesh-201015	Report No: HLPL20-260420-01
Description: Vijaysar Herbal Wood Tumbler	Reporting Date: 27.04.2026
Sample Qty.: 1 Sample	Sample Received On: 20.04.2026
	Sampled By: Customer
	Analysis Start Date: 20.04.2026
	Analysis End Date: 27.04.2026

Page No: 01 of 01

TEST RESULTS

S.No.	Test Parameters	Unit	Test Result	Test Method
	Appearance	-	Light Brown	Visual
2.	Organic Matter	%	Original Value	HLPL/STP/EQP/02
3.	Moisture Content	%	14.32	HLPL/STP/EQP/02
4.	pH	-	5.79	HLPL/STP/EQP/09
5.	Average Fiber Length	mm	15.90	HLPL/STP/EQP/62
6.	Toxicity	-	Non toxic	HLPL/STP/EQP/12
7.	Biodegradability	-	Yes	HLPL/STP/EQP/12
8.	Electrical Conductivity	dS/m	0.007	HLPL/STP/EQP/07
Chemical Composition				
1	Cellulose	%	44	HLPL/STP/EQP/12
2	Lignin	%	26	HLPL/STP/EQP/12
3	Hemicellulose	%	30	HLPL/STP/EQP/12

Note: 1. The tumblers are made from pure, natural Vijaysar herbalwood.

2. Identification Test/Indicator: When filled with water, genuine Vijaysar wood turns

The water a light reddish-brown Color after 8-10 hours, indicating the release of natural compounds.

End of Report



बिना होलोग्राम के रिपोर्ट
मान्य नहीं है



Note:-
• The result indicated only refer to the tested samples and listed parameters and do not endorse any product.
• Total liability of the laboratory is limited to the invoiced amount.
• This certificate shall not be reproduced wholly or in part without prior written consent of the laboratory.
• Samples received shall be destroyed after four weeks from the date or issue of the certificate unless specified otherwise.
• This certificate shall not be used in any advertising media or as evidence in the Court of Law without prior written consent of the laboratory.

Branch Office: C-15/15, Turner Road, Muskan Chowk, ISBT Dehradun 248001 Uttarakhand, India